CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

CEMENT CONCRETE FLOORING TILES

Lab ID	:	**CP-2017-05-09-01** **Date: 12-05-17**
Customer	:	Assistant Executive Engineer, Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing open gym parks of Judicial Layout of Ward no.04
Agency	:	Technical Manager (West)KRIDL, Bangalore
Customer Reference	:	EE(Project)/ Ynk Zone/WO/40/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-05-17
Sample ID No	:	2017-05-09-01-02
Sample Type/ Size	:	Pre-Polished Designer Cement Concrete Tiles
Reference to BIS codes	:	IS 1237:2012
Date of test	:	09-05-17

1.Wet Transverse Strength

Sl.No.	Dimension (mm)			Wet Transverse Strength	Average	Requirement as per IS:1237-2012
	L	B	T	(N/mm^2)	(N/mm^2)	
1	400	400	25.34	7.54	7.42	The average wet transverse strength shall not be less than $3N/mm^2$.
2	399	400	24.48	6.98		
3	400	400	25.57	7.84		
4	399	400	25.28	7.64		
5	400	399	25.22	7.25		
6	400	400	25.28	7.28		

2. Water Absorption

Sl.No.	Dimension (mm)			Water Absorption	Average	Requirement as per IS:1237-2012
	L	B	T	(%)	(%)	
1	399	400	25.38	2.65	2.84	The average percentage of water absorption shall not exceed 10.
2	400	400	25.12	2.41		
3	401	399	25.18	3.08		
4	400	400	25.19	3.45		
5	399	400	25.28	2.98		
6	400	401	25.17	2.47		

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signature
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: T- 4358

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2017-05-08-08** **Date: 10-05-17**
Customer	:	Assistant Executive Engineer, Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing open gym parks of Judicial Layout of Ward no.04
Agency	:	Technical Manager (West)KRIDL, Bangalore
Customer's Reference	:	EE(Project)/ Ynk Zone/WO/40/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-05-17
Sample ID No	:	2017-05-08-08-01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	09-05-17

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.76	–
2	Finess by Air permeablity method (m^2/kg, Min)	266.6	225m^2/kg, Min
3	Density (gm/cc)	3.18	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	175 minutes	Not less than 30 minutes
6	Final Setting time	290 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	2mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2017-05-08-08** **Date: 06-06-17**
Customer	:	Assistant Executive Engineer, Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing open gym parks of Judicial Layout of Ward no.04
Agency	:	Technical Manager (West)KRIDL, Bangalore
Customer's Reference	:	EE(Project)/ Ynk Zone/WO/40/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-05-17
Sample ID No	:	2017-05-08-08-01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	09-05-17

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.5N/mm^2	Not less than 37 N/mm^2
3	28 Days	55.0N/mm^2	Not less than 53 N/mm^2

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2017-05-08-08** **Date: 11-05-17**
Customer	:	Assistant Executive Engineer, Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing open gym parks of Judicial Layout of Ward no.04
Agency	:	Technical Manager (West)KRIDL, Bangalore
Customer's Reference	:	EE(Project)/ Ynk Zone/WO/40/2016-17
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	08-05-17
Sample ID No	:	2017-05-08-08-02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	08-05-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Reqũired as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	1031	1031	6.9	93.1	90-100
3	20 mm	5113	6144	41.0	59.0	30-70
4	10 mm	4192	10336	68.9	31.1	10-35
5	4.75 mm	3973	14309	95.4	4.6	0-5
6	Pan	691	15000	100.0	0	---

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO Sig..... Date..... BANGALORE

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-05-08-08** **Date: 11-05-17**

Sample ID No : 2017-05-08-08-02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.8	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	14.2	
3	Specific Gravity	2.6	_
4	Bulk Density(Loose) (Kg/l)	1.54	_
5	Bulk Density(Compacted) (Kg/l)	1.56	_
6	Water Absorption(%)	0.21	_

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2017-05-08-08** **Date: 11-05-17**
Customer	:	Assistant Executive Engineer, Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing open gym parks of Judicial Layout of Ward no.04
Agency	:	Technical Manager (West)KRIDL, Bangalore
Customer Reference	:	EE(Project)/ Ynk Zone/WO/40/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-05-17
Sample ID No	:	2017-05-08-08-02(b)
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	08-05-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	359	359	7.2	92.8	90-100
3	10 mm	1927	2286	45.7	54.3	25-55
4	4.75 mm	2233	4519	90.4	9.6	0-10
5	Pan	481	5000	100	0	–

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO BANGALORE Sig..... Date.....

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-05-08-08** **Date: 11-05-17**

Sample ID No : 2017-05-08-08-02(b)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.7	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.9	
3	Specific Gravity	2.58	–
4	Bulk Density(Loose) (Kg/l)	1.55	–
5	Bulk Density(Compacted) (Kg/l)	1.59	–
6	Water Absorption(%)	0.22	–
7	Aggregate crushing Value(%)	23.6	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	24.7	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID	:	**CP-2017-05-08-08** **Date: 11-05-17**
Customer	:	Assistant Executive Engineer, Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing open gym parks of Judicial Layout of Ward no.04
Agency	:	Technical Manager (West)KRIDL, Bangalore
Customer's Reference	:	EE(Project)/ Ynk Zone/WO/40/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-05-17
Sample ID No	:	2017-05-08-08-03
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	08-05-17
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	83	83	8.3	91.7	90-100	90-100	90-100	95-100
3	2.36 mm	144	227	22.7	77.3	60-95	75-100	85-100	95-100
4	1.18 mm	188	415	41.5	58.5	30-70	55-90	75-100	90-100
5	600 micron	176	591	59.1	40.9	15-34	35-59	60-79	80-100
6	300 micron	154	745	74.5	25.5	5-20	8-30	12-40	15-50
7	150 micron	165	910	91.0	9.0	0-10	0-10	0-10	0-15
8	Pan	90	1000	100.0	0.0	---	---	---	---
Result :The tested Sample Conforms to Grading Zone II									

CIVIL Pro Sig..... Date..... BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: T- 4358

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-05-17-11** **Date: 20/05/2017**

Customer : Assistant Executive Engineer, Project Sub Division Yelahanka Zone, BBMP, Bangalore.

Address : Project Sub Division Yelahanka Zone, BBMP, Bangalore.

Project Name : Providing open gym parks of Judicial Layout of Ward no.04

Agency : Technical Manager (West)KRIDL, Bangalore

Customer's Reference : EE(Project)/ Ynk Zone/WO/40/2016-17

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-05-17

Sample ID No : 2017-05-17-11-01

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 20/05/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	13/05/2017	20/05/2017	150.37 X 150.40 X 150.27	22616	8.331	409.3	18.1	18.4
2	PCC	M20	13/05/2017	20/05/2017	150.31 X 150.38 X 150.25	22604	8.341	415.9	18.4	
3	PCC	M20	13/05/2017	20/05/2017	150.24 X 150.29 X 150.31	22580	8.315	420.0	18.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

TEST REPORT OF CEMENT CONCRETE KERB STONE

Lab ID	:	**CP-2017-05-09-01** **Date: 13-05-17**
Customer	:	Assistant Executive Engineer, Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division Yelahanka Zone, BBMP, Bangalore.
Project Name	:	Providing open gym parks of Judicial Layout of Ward no.04
Agency	:	Technical Manager (West)KRIDL, Bangalore
Customer's Reference	:	EE(Project)/ Ynk Zone/WO/40/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-05-17
Sample ID No	:	2017-05-09-01-01
Sample Type /Size	:	CC Kerb Stone/ 450*165*400mm
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete
Date of test	:	09/05/2017

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	Kg	(Sq.mm)	(KN)	(N/mm2)	(N/mm2)	(N/mm2)
1	A	100.03	165.54	8.864	7857	143.1	18.2	16.9	21.2
2	B	100.05	165.51	8.793	7860	142.2	18.1	18.1	22.6
3	C	100.02	165.50	8.815	7856	144.1	18.3	18.3	22.9

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |